

SURGICRYL[®]


PGA

POLYGLYCOLIC ACID

SURGICRYL[®]
PGA
POLYGLYCOLIC ACID



Type	Braided and coated multifilament
Composition	Polyglycolic acid
Coating	Polycaprolactone and calcium stearate (1%)
Colour	Violet / Beige - undyed
Tissue reaction	Minimal
Absorption	The hydrolytic action by which the material is broken down results in total absorption in approximately 60 to 90 days. Approximately 50% of tensile strength remain after 21 days.
Presentation	Box with 12 sutures



*For quality
&
safety*

smi

www.sutures.be

SURGICRYL[®]

PGA
POLYGLYCOLIC ACID

CHARACTERISTICS

- ✓ High tensile strength
- ✓ Synthetic
- ✓ Breaks down by hydrolysis
- ✓ Braided structure
- ✓ Coated multifilament
- ✓ Hermetically sealed packing

INDICATIONS General soft tissue closing and/or ligation
especially in General surgery
Skin closure
Gastrointestinal surgery
Gynaecology
Obstetrics
Plastic surgery
Urology
Ophthalmic surgery
Orthopaedics

BENEFITS

Excellent tissue support
Minimal tissue reaction
Predictable absorption rate
Excellent handling properties
High flexibility
High tensile strength
Excellent knot security
Soft passage through the tissues with minimal sawing, tissue drag and trauma
Good knot tie down / adjustability
Reduced capillary action
Guaranteed seal and product sterility

CONTRAINDICATIONS Cardiovascular surgery
Neurosurgery
Being absorbable not to use when an extended wound support is required.
Caution in patients with delayed wound healing (e.g. compromised immune system).